

## MATERIAL DATA SHEET

### Material description:

**High-temperature bonding agent K 84** - is a ready-to-use, high-temperature bonding agent for refractory insulating materials up to 1000 °C. It is also suitable for bonding lightweight structural systems of calcium silicate boards PROMASIL®.

### Specifications:

Designation and type:	<b>High-temperature bonding agent K 84</b>
Colour:	grey
Consistency:	pasty
Classification temperature:	1000 °C
Processing temperature:	10 – 20 °C
Setting after application:	8 h
Hardening after application:	24 h
Full hardening after application:	1 week
Storage:	the date of consumption is indicated on the packaging frost-free
Packaged units:	23 g / 310 ml / 1 - 7,5 - 15 kg

All details correspond to the state of technology and have been described to the best of our knowledge. Changes on the base of new results are possible. Data in material data sheet are higher priority, that data in catalogue.

Last revision: 8/2021