

Arno Witgert OT Wahnscheid 56414 Herschbach/Oww.

Propec



### Technical data sheet

Raw material no. **600 (s)/G 12 (l)** Firing temperature: **1000-1150°C**

Name: **Steinzeug-Gießmasse schwarz**

	1000°C	1100°C	1200°C	1300°C
Firing shrinkage:	-0,6 %	6,4 %		
Total shrinkage	3,4 %	10,2 %		
Water absorption:	21,7 %	7,2 %		

Firing colour: brown brown-black

Coefficient of thermal expansion at different firing temperatures in 10<sup>-6</sup> m/(m x K)

	1000°C	1100°C	1200°C	1300°C
WAK <sub>20-400°C</sub> :	6,1	8,6		
WAK <sub>20-500°C</sub> :	6,6	9,2		
WAK <sub>20-600°C</sub> :	8,2	11,1		

Chemical analysis (calcined)

SiO <sub>2</sub>	72,3 %
Al <sub>2</sub> O <sub>3</sub>	16,5 %
TiO <sub>2</sub>	1,0 %
Fe <sub>2</sub> O <sub>3</sub>	4,9 %
CaO	0,2 %
MgO	0,4 %
Na <sub>2</sub> O	0,2 %
K <sub>2</sub> O	2,9 %
GV	( 4,2 % )

Dry shrinkage:	4,0 %	Viscosity (acc. to Lehmann) (s):	21
		Thixotropy (acc. to Lehmann) (s):	6
Modulus of rupture:	1,1 N/mm <sup>2</sup>	Thickness of body after 15 min (mm):	4,9 after 45 min: 5,3
		Demoulding time after 15 min (min):	45 90
Need of water:	49,5 %	Litre weight (g):	1750

GROUND POWDER no. 600: 100 % Casting slip powder are stirred in ca. 38 % water that contains 0.1 % Dolaflox SP 11 and 0.2 % Gießfix 162. After homogenisation the body should stay for 2-3 h. In this time you could stir slowly. Impurities must sieved out.

LIQUID SLURRY no. G 12: The Slurry must be stirred before casting without stirring air bubbles inside. If the viscosity is too high you could add some deflocculant, e. g. LIQUI-FIX of WITGERT.

The body contains deflocculants.

The data are average values. Sale is carried out according to pattern and to our terms and conditions.

Tone und Fertigmassen in allen Naturfarben: geschnitzelt gemahlen gewalzt granuliert  
Plastisch flüssig Kaoline Mangantone und -oxide Schamotten Sinterengoben

Fachberatung durch Keramik-Ingenieure  
Eigenes Labor

Arno Witgert, Telefon 0049 (0) 6435 / 9223-0  
Inh. Dipl.-Ing. (FH) Michael Liebig e. K. Telefax 0049 (0) 6435 / 9223-33  
OT Wahnscheid E-Mail witgert@witgert.de  
D - 56414 Herschbach Internet http://www.witgert.de

Banken  
KSK Ransbach-Baumbach/Ww., Konto-Nr. 040000309 (BLZ 570 510 01)  
Nass. Sparkasse Wallmerod, Konto-Nr. 982 004 403 (BLZ 510 500 15)